



Postal Certification

Clysar EZ

Clysar® EZ and Clysar EZF (F stands for center-folded film. No change to the formulation of manufacturing process) are multilayer polyolefin-based shrink films that meet USPS polywrap requirements for mail pieces that are mailed at automation-flat rates.

Property		Range	Test Method	Target
1a.	Kinetic Coefficient of Friction, MD Film on Stainless Steel w/ No. 8 Mirror Finish	<0.45	ASTM D1894	0.21
1b.	Kinetic Coefficient of Friction, MD Film on Film	0.20-0.55		0.20
2	Haze	<70	ASTM D1003	Max. 3
3a.	Secant Modulos, 1% Elongation TD	>50,000 psi	ASTM D882	77,000
3b.	Secant Modulos, 1% Elongation TD	>40,000 psi		77,000
4	Nominal gauge	>0.001 in	ASTM D374	0.0011
5	Static Charge	<2.0 kV	ASTM D4470	0.2
6	Blocking	<15 g	ASTM D3354	5

The above information is to the best of our knowledge reliable as of the date compiled. No representation, warranty or guarantee is made as to accuracy or completeness. We do not accept liability for any loss or damage that may occur from the use of this information as it is the user's responsibility to satisfy themselves for their own particular use. 2/07